



Kingfield Gel-Flex Composite Waterproofing Systems

Chemically resistant polymer adhesive Seaming Tape - Seaming Tape for GFG series sheet membranes

ADVANTAGES

Durotape is a 35 mil, VOC free, cold applied coating designed to provide protection against water intrusion and soil contaminants on below grade substrates.

Durotape, combined with strong, flexible film backing, provides a protective coating with cohesive strength and durability that conforms well to irregular shapes.

Durotape has the ability to remain flexible while maintaining a water-tight seam. It is chemically resistant and is exceptionally adhesive.

Durotape has an integrated primer in the adhesive, which allows for faster application at temperatures above 40°F on clean, dry substrates.

ADVANTAGES

100% solids

Maintains volume to ensure a watertight bond.

Excellent adhesion

Primer is unnecessary for fast and easy application.

Maintains flexibility

800% elongation dynamically responds to movement, thermal expansion, and contraction to maintain a watertight bond.

Easy workability

Applies and adheres in cold temperatures.
Trims cleanly.

Superior chemical resistance Resistant to hydrocarbon and soil contaminants, Durotape retains its physical properties in the harshest environments ensuring long term effectiveness.

* Contact Kingfield for temperatures below 40°F to determine whether a primer is required.

DUROTAPE	CHARACTERISTICS	DUROTAPE PROPERTIES	RESULTS	TESTING METHOD
Appearance	Green backing - Grey adhesive - Clear liner	Total Thickness	35 mils	ASTM D1000
Roll Dimensions	4 inches x 50 feet	Backing Thickness	7 mils	ASTM D1000
Weight	4.66 lb/roll	Adhesive Thickness	28 mils	ASTM D1000
Solids Content	100%	Tensile Strength	14 lb/in	ASTM D1000
Service Temperature Range	-20°F to +125°F	Elongation	800%	ASTM D1000
Leachable Chlorides	None	Impact Resistance	20 in lb (double wrap)	ASTM G14
		Water Vapor Transmission Rate	<0.005 g/(24h*100 in ²)	ASTM E96 Method B
		Water Absorption	<0.5%	ASTM D570

APPLICATIONS

- Durotape is used to seam the Hydrogel Gel-Flex and Turbo-Seal Gel-Flex waterproofing GFG Series sheet membranes.
- The flexible backing makes it a good coating for hand wrapping. Appropriate for coating and reconditioning small to moderate diameter pipe, bends, tees, and metal structures, as a single component coating below grade.
- Always ensure that the surface of the sheet membrane is clean and dry before installation of Durotape.

SEAMING INSTRUCTIONS — SHEET WATERPROOFING MEMBRANE

- Overlap membrane by a minimum 2 inches. Install tape onto seam by removing release liner and using roller to firmly press tape onto seam.

DETAILING INSTRUCTIONS — SHEET WATERPROOFING MEMBRANE

- Apply tape over the surface of the seam on both the horizontal and vertical sections of the detail reinforcement sheet. Install Durotape 2 inches from the edge of each horizontal edge, wrapping tape around all extrusions and corners to ensure a tight sandwich bond of the membrane and substrate.

STORAGE

- Keep in Dry Storage out of direct heat and sunlight.
- Store between 50-80 degrees Fahrenheit.

HEALTH AND SAFETY

Consult the MSDS

KINGFIELD CONSTRUCTION PRODUCTS

Minneapolis, Minnesota

www.kingfieldcpc.com

TECHNICAL SUPPORT

Phone: +1 (612) 225-5167

Email: info@kingfieldcpc.com

©2014 Kingfield

Printed in U.S.A.

GFG4 PRODUCT DATA SHEET – v4.09.15.14

LIMITED WARRANTY NOTICE Every reasonable effort is made to apply KINGFIELD CONSTRUCTION PRODUCTS (KCP) exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, KCP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and KCP shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the KCP Technical Manager.

This information and all further technical advice are based on KCP's present knowledge and experience. However, KCP assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, KCP disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. KCP SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. KCP reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.